Laminated Plywood (TFL / Melamine)

Hardwood plywood core, white or black melamine face both sides

INDICATIVE DATA — please contact us directly for the manufacturer's spec sheet for your specific order: 718-386-6119 · inquiry@dmlumber.com

Plywood panels with a white or black melamine face (thermally fused laminate, TFL) fused front and back, so both faces arrive finished. Also called TFL plywood, melamine plywood or melamine-faced plywood.

Range

Face	Thickness	Panel
White melamine (both sides)	1/2" (12 mm) · 3/4" (18 mm)	4' x 8' (1220 x 2440 mm)
Black melamine (both sides)	1/2" (12 mm) · 3/4" (18 mm)	4' x 8' (1220 x 2440 mm)

Core panel

Item	Data
Product	Hardwood plywood, veneer core
Species	Albizia falcataria and combi core
Veneer grades	C2 / B2 / B / B / A

Formaldehyde emission compliance

Standard	Category	Limit	Status
California CARB ATCM 93120 (Phase 2)	Hardwood plywood, veneer core	0.05 ppm	Certified by a CARB-approved third-party certifier
US EPA TSCA Title VI (40 CFR Part 770)	Hardwood plywood, veneer core	0.05 ppm	Certified by an EPA-recognized third-party certifier

Certified construction: urea formaldehyde (UF) glue, 3 and 5 plies and up, 6.0 to 19.0 mm; phenol formaldehyde (PF) glue, 3 and 5 plies and up, 6.0 to 15.0 mm. Testing by the primary method, ASTM E 1333, with quarterly on-site inspection by the certifier.

Certificates of conformity are available on request: 718-386-6119 · inquiry@dmlumber.com.