



# Sanded Plywood ACX, BCX, CpC

Plantation-grown radiata pine

**INDICATIVE DATA** — please contact us directly for the manufacturer's spec sheet for your specific order: 718-386-6119 · inquiry@dmlumber.com

## Features

- Manufactured with 100% radiata pine plantation grown logs
- FSC® certification available · TSCA certified
- Made with phenolic exterior bioadhesive / WBP (water boiled proof), exempt from CARB regulations
- Highly resistant plywood, Timber Products Inspection stamped, meets requirements of PS 1-09 underlayment
- Extra smooth sanded finish, 150 grit face suitable for staining or painting
- Sustainable

## Applications

- Table and counter tops
- Underlayment
- Industrial applications
- Packaging
- Furniture
- Construction
- Lamination base

## Face veneer grade

**A****B****Cp**

## General properties

| Property              | Value                                  | Standard      |
|-----------------------|----------------------------------------|---------------|
| Glue                  | Bioadhesive / WBP (water boiled proof) | PS1           |
| Formaldehyde emission | < 0.020 ppm                            | ASTM E1333-14 |
| Glue quality          | Outdoor environment                    | PS1           |
| Available grades      | AC   BB   BC   CpC                     | PS1           |

## Technical specification

| Nominal thickness (mm) | 3.2   | 4.2   | 5.2   | 6     | 9     | 12    | 15    | 18    | 21    | 25    | 30    |
|------------------------|-------|-------|-------|-------|-------|-------|-------|-------|-------|-------|-------|
| Nominal thickness (in) | 1/8   | 1/6   | 1/4   | 1/4   | 11/32 | 15/32 | 19/32 | 23/32 | 13/16 | 1/1   |       |
| No. of plies           | 3     | 3     | 3     | 3     | 3/5   | 5     | 5/7   | 7/9   | 7     | 9     | 11    |
| Pieces per bundle      | 270   | 230   | 170   | 160   | 108   | 80    | 65    | 54    | 47    | 39    | 33    |
| Sheet weight (lbs)     | 12    | 15    | 17    | 20    | 30    | 39    | 50    | 59    | 69    | 80    | 98    |
| Bundle weight (lbs)    | 3152  | 3174  | 3240  | 3152  | 3196  | 3152  | 3196  | 3196  | 3240  | 3108  | 3240  |
| M3                     | 2.572 | 2.798 | 2.941 | 2.858 | 2.893 | 2.858 | 2.902 | 2.893 | 2.938 | 2.902 | 2.947 |

Size: 8' x 4' (length x width). **Bending strength** > 40 N/mm<sup>2</sup> · **Tensile strength** > 0.8 N/mm<sup>2</sup> · **Moisture** 8 - 12% · **Density** 450 - 550 kg/m<sup>3</sup>